Coated papers

Coated Satinated White Office Pa Creative

MAC149 Top Coated Graphic⁺ Silk - FSC[®] 150 g/m²

Description	smooth surface pro runnability. Certified		•	ır images. The consister	nt paper qua	ality delivers excellent
Physical Properties	Weight (g/m ²⁾	150	ISO 536	Whiteness	127	CIE
	Thickness (µm)	135	ISO 534	Opacity (%)	95.5	Elrepho
	Brightness (%)	100	ISO 2470-2	Gloss Tappi 75º (%)	27	ISO 8254-1
Features			•	ed Graphic⁺ Silk the idea t mail, magazines and p		••
Available Sizes	SRA	3				
	Grain SG direction					
	LG = Long grain, SG = Short grain					
Storage Conditions	Temperature 10 - 30 °C, Relative Humidity 20 - 70% Repack opened reams or boxes when not in use.					
Print Conditions	Acclimatize paper 24 hours before printing in print room conditions (preferably next to printer) Best results are obtained between 15-25 °C and 30-65% RH (relative humidity)					
Environment, Health & Safety	No Material Safety Data Sheet required. ISO 9001 and 14001 certified production site. ECF (Elemental Chlorine Free) bleaching technique for wood pulp. Paper waste is suitable for recycling in most countries. Please refer to local paper recycle station.					
Processing Guidelines, Tips & Tricks		rioPrint i-S	Series. Testing of o	customer application is	always advi	sed to secure proper
Environmental Certification	FSC www.fsc.org	colabel	\bigotimes			



Standard disclaimer: All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.

Canon Inc. canon.com Canon Europe canon-europe.com English edition © Canon Europa N.V., 2018

