

Toner
CrystalPoint
WaterBased Ink
UV Curable
Latex

## Uncoated Papers

# LFM116 Top Label Paper - FSC®

## 75 g/m<sup>2</sup>

### Product Description

A high white, smooth, FSC-certified, uncoated paper for high quality drawings and posters.

### Physical Properties

Weight	75 g/m <sup>2</sup>	ISO 536	Brightness D65/10°	113 %	ISO 2470
Opacity	93 %	ISO 2471	Whiteness CIE D65/10	168 %	ISO 11475
Bulk	1,39 cm <sup>3</sup> /g	ISO 534	Roughness	200 ml/min	Bendtsen ISO 8791-2

All values listed are target values

### Applications/features

High quality CAD drawings and Posters

FSC certified  
EU Ecolabel  
ISO 9706 standard for permanence  
EMAS certified  
ISO 14001 certified

### Available Widths (mm)

3" core	297	420	594	620	841	914				
---------	-----	-----	-----	-----	-----	-----	--	--	--	--

Refer for our current offering to [www.canon-europe.com/mediaguide](http://www.canon-europe.com/mediaguide)

### Storage Conditions

Shelf life: 2 years, Temperature 21°C, Relative Humidity 50%  
Repack opened rolls when not in use. Allow material to adapt to room conditions for 24 hours before printing.

### Print Conditions

Best results are obtained between 20-27°C and 30-60% RH.  
Refer also to printer specifications.

### Environment, Health & Safety

No Material Safety Data Sheet required. Paper waste suitable for recycling.

### Lamination Compatibility

Cold	Warm	Hot	Cold: pressure sensitive Warm: heat activated: 85°C - 95°C Hot: heat activated: 105°C -130°C
yes	No	no	

### Outdoor Use

This uncoated paper is developed for indoor use.

### Colour Profiles

Canon develops high-quality colour profiles for media / ink / printer / RIP combinations.  
Check availability of profiles for your printer on [www.canon-europe.com/mediaguide](http://www.canon-europe.com/mediaguide)

### Environmental Certification



---

## Processing Guidelines

### Printing guidelines

Allow material to adapt to room conditions for 24 hours before printing. It is recommended to handle the media with cotton gloves. Make sure that the media comes not into contact with grease, oil, silicon, and dirt to avoid printing defects. Insert media with care in the printers. Incorrect loading can cause skewing or creasing. Allow material to adapt to room conditions for 24 hours before printing. It is recommended to calibrate the printer before printing and to make a test print. Print results will vary for different printers.

Ink/toner restrictions and printer settings have to be set for specific printers to obtain the best results. Canon colour profiles include recommended ink restrictions and printer settings for Canon supported printers.

### Application guidelines

When laminating CrystalPoint® prints pressure sensitive laminates are recommended. A laminator with soft rubber rollers is preferred. For optimal results temperature should be set between 55-60°C.

#### Standard disclaimer:

All specifications subject to change without notice. All company and/or product names are trademarks and/or registered trademarks of their respective manufacturers in their markets and/or countries.